

Hauthaway										<i>Established 1852</i>				
Hauthane Polyurethane Dispersions														
Disinfectant Agent Spot Resistance Tests - Elevated Temperature Cured (80°C for 15 minutes)														
	1 Hr					6 Hr					24 Hr			
Grade + Crosslinker	Purell	Lysol	Ethanol	IPA		Purell	Lysol	Ethanol	IPA		Purell	Lysol	Ethanol	IPA
Hauthane L-3369 + 3% Aziridine	5	5	5	5		4	5	4	4		5	5	4	4
Hauthane L-3369 + 8% Isocyanate	4	5	5	5		4	5	4	4		4	4	3	4
Hauthane L-3369 + 6% Carbodiimide	4	5	4	4		4	4	4	4		4	4	4	4
Hauthane L-3838 + 3% Aziridine	5	5	5	5		5	5	5	5		4	5	5	5
Hauthane L-3838 + 8% Isocyanate	4	5	4	5		4	5	4	5		4	5	4	4
Hauthane L-3838 + 6% Carbodiimide	4	5	4	5		4	5	4	5		4	5	4	5
5 = No effect														
1 = Dissolved Film														

