micropowders.com

NatureFine R331

Finely micronized rice bran wax for use in industrial coatings and agrochemical products

Features and Benefits

- Natural wax
- Excellent burnish and abrasion resistance compared to synthetic wax additives
- Biodegradable to OECD 302C test standard
- Improves lubricity, dust-off, and block resistance in seed coatings
- Effective dry powder binding agent
- Microplastic alternative

Composition

Rice bran wax

Recommended Addition Levels

1.0 - 20.0% (on total formula weight)

Systems and Applications

Seed coatings and other agricultural products. Granulation aid. High biocontent coatings. Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings interior and exterior can and container coatings; coil coatings.

Typical Properties*

NatureFine R331

Melting Point °C 77 - 82

Density @ 25 °C (g/cc) 0.96

Mean Particle Size (µm) 6.0 - 10.0

Maximum Particle Size (µm) 31.00

Apr-20