

SYNTRAN® 1930

Technical Information

SYNTRAN® 1930 is based on our proprietary hybrid acrylic technology. This technology creates a film with very high gloss, resistances, and fast dry times. This technology also allows for excellent adhesion over multiple substrate types.

Performances

Applications	Floor Finish Metal Coatings
Features and Benefits	Faster dry times Film has high gloss, hardness with good buffability Hydroxyl Functional Low VOC requirements to formulate coating

Typical Chemical and Physical Properties (all testing done at 22°C, unless specified)

Physical form	Milky dispersion
Solids content	38%
pH value	8.5
Viscosity	1000 cps
Density	1.054
MFFT	65°C
Freeze-thaw stability	Protect from freezing
Stability at 52°C	Unchanged after 30 days

Safety, Storage, Handling

Please refer to Safety Data Sheet. Shelf life: 12 months from shipping date in originally sealed containers.
Storage: between 5°C and 35°C.