

SYNTRAN® 1950C

Technical Information

SYNTRAN® 1950C is based on our unique styrenated acrylic technology. This technology creates a film with very high gloss, and fast dry times. This technology also allows for excellent adhesion over multiple substrate types.

Performances

Applications Floor Finish and Household

Label, board and packaging coatings (OPV)

Features and Benefits Faster dry times

Excellent adhesion to multiple substrates

Film has very high gloss, hardness with good printability

Low VOC requirements to formulate coating

FDA 175.105, 175.300, 175,320, 176.170, 176.180, 177.1010, 178.3790 approved

Typical Chemical and Physical Properties (do not constitute specifications)

Physical form Milky dispersion

 Solids content
 40.0%

 pH value
 7.5

 Viscosity
 40 cps

 Density @22°C
 1.060

 MFFT
 55°C

Freeze-thaw stability Unchanged after 3 cycles
Stability at 52°C Unchanged after 30 days

Safety, Storage, Handling

Please refer to Safety Data Sheet.

Shelf life: 12 months from shipping date in originally sealed containers.

Storage: between 5°C and 35°C.

April 20 / Page 1 of 1